

Supplier Tin Finish Required Information

What is the finish type (immersion, electroplate etc)?	Electroplate
What is the plating thickness?	300-800uinchs
Is the finish matte or bright (please provide grain size)?	Matte (Grain size: 3-10um)
What is the base metal of the termination?	Copper base metal
Is there a nickel barrier layer present (please provide thickness)?	No
What is the annealing process, if any, used?	Annealing bake @ $155 \pm 5^{\circ}\text{C}$ for 1.75hrs (include 0.75hr warming time) within 24hrs after plating.
Are any other tin whisker risk mitigation practices used on this device?	Routine QA monitoring
Are any alternative finishes other than pure tin available (NiPdAu preferred)?	None